

Type	No.	China GB	JIS	AST M	Chemical composition %										
					C	Si	Mn	P	S	Ni	Cr	Mo	Cu	N	other
Austenitic stainless steel	1	1Cr17Mn6Ni5N	SUS201	201	≤0.15	≤1.00	5.50-7.50	≤0.060	≤0.030	3.50-5.50	16.00-18.00	-	-	≤0.25	-
	2	1Cr18Mn8Ni5N	SUS202	202	≤0.15	≤1.00	7.50-10.00	≤0.060	≤0.030	4.00-6.00	17.00-19.00	-	-	≤0.25	-
	3	1Cr18Mn10Ni5Mo3N			≤0.15	≤1.00	8.50-12.00	≤0.060	≤0.030	4.00-6.00	17.00-19.00	2.8-3.5	-	0.20-0.30	-
	4	1Cr17Ni7	SUS301	301	≤0.15	≤1.00	≤2.00	≤0.065	≤0.030	6.00-8.00	16.00-18.00	-	-	-	-
	5	1Cr18Ni9	SUS302	302	≤0.15	≤1.00	≤2.00	≤0.035	≤0.030	8.00-10.00	17.00-19.00	-	-	-	-
	6	Y1Cr18Ni9	SUS303	303	≤0.15	≤1.00	≤2.00	≤0.20	≤0.030	8.00-10.00	17.00-19.00	1)	-	-	-
	7	Y1Cr18Ni9Se	SUS303Se	303Se	≤0.15	≤1.00	≤2.00	≤0.20	≤0.030	8.00-10.00	17.00-19.00	-	-	-	Se≥0.15
	8	0Cr18Ni9	SUS304	304	≤0.07	≤1.00	≤2.00	≤0.035	≤0.030	8.00-10.00	17.00-19.00	-	-	-	-
	9	00Cr19Ni10	SUS304L	304L	≤0.030	≤1.00	≤2.00	≤0.035	≤0.030	8.00-10.00	18.00-20.00	-	-	-	-
	10	0Cr19Ni9N	SUS304N1	304N	≤0.08	≤1.00	≤2.00	≤0.035	≤0.030	7.00-10.50	18.00-20.00	-	-	0.10-0.25	-
	11	0Cr18Ni10NbN	SUS304N2	XM21	≤0.08	≤1.00	≤2.00	≤0.035	≤0.030	7.50-10.50	18.00-20.00	-	-	0.15-0.30	Nb≤0.15
	12	00Cr18Ni10N	SUS304LN	-	≤0.030	≤1.00	≤2.00	≤0.035	≤0.030	8.50-11.50	17.00-19.00	-	-	0.12-0.22	-
	13	1Cr18Ni12	SUS305	305	≤0.12	≤1.00	≤2.00	≤0.035	≤0.030	10.50-13.00	17.00-19.00	-	-	-	-
	14	0Cr23Ni13	SUS309S	309S	≤0.08	≤1.00	≤2.00	≤0.035	≤0.030	12.00-15.00	22.00-24.00	-	-	-	-
	15	0Cr25Ni20	SUS310S	310S	≤0.08	≤1.00	≤2.00	≤0.035	≤0.030	19.00-22.00	24.00-26.00	-	-	-	-
	16	0Cr17Ni12Mo2	SUS316	316	≤0.08	≤1.00	≤2.00	≤0.035	≤0.030	10.00-14.00	16.00-18.50	2.00-3.00	-	-	-
	17	1Cr18Ni12Mo2Ti <sup>6)</sup>			≤0.12	≤1.00	≤2.00	≤0.035	≤0.030	11.00-14.00	16.00-19.00	1.80-2.50	-	-	Ti5(C%-0.02)~0.08
	18	0Cr18Ni12Mo2Ti	SUS316Ti	316Ti S3163	≤0.08	≤1.00	≤2.00	≤0.035	≤0.030	11.00-14.00	16.00-19.00	1.80-2.50	-	-	Ti5*C%-0.70
	19	00Cr17Ni14Mo2	SUS316L	316L	≤0.030	≤1.00	≤2.00	≤0.035	≤0.030	12.00-15.00	16.00-18.00	2.00-3.00	-	-	-
	20	0Cr17Ni12Mo2N	SUS316N	316N	≤0.08	≤1.00	≤2.00	≤0.035	≤0.030	10.00-14.00	16.00-18.00	2.00-3.00	-	0.10-0.22	-
	21	00Cr17Ni13Mo2N	SUS316LN	316LN	≤0.030	≤1.00	≤2.00	≤0.035	≤0.030	10.50-14.50	16.00-18.50	2.00-3.00	-	0.12-0.22	-

Type	No.	China GB	JIS	AST M	Chemical composition %										
					C	Si	Mn	P	S	Ni	Cr	Mo	Cu	N	other
Austenitic stainless steel	22	0Cr18Ni12Mo2Cu2	SUS316J1	-	≤0.08	≤1.00	≤2.00	≤0.035	≤0.030	10.00-14.50	17.00-19.00	1.20-2.75	1.00-2.50	-	-
	23	00Cr18Ni14Mo2Cu2	SUS316J1L	-	≤0.030	≤1.00	≤2.00	≤0.035	≤0.030	12.00-16.00	17.00-19.00	1.20-2.75	1.00-2.50	-	-
	24	0Cr19Ni13Mo3	SUS317	317	≤0.12	≤1.00	≤2.00	≤0.035	≤0.030	11.00-15.00	18.00-20.00	3.00-4.00	-	-	-
	25	00Cr19Ni13Mo3	SUS317L	317L	≤0.08	≤1.00	≤2.00	≤0.035	≤0.030	11.00-15.00	18.00-20.00	3.00-4.00	-	-	-
	26	1Cr18Ni12Mo3Ti <sup>6)</sup>			≤0.12	≤1.00	≤2.00	≤0.035	≤0.030	11.00-14.00	16.00-19.00	2.50-3.50	-	-	Ti5(C%-0.02)~0.08
	27	0Cr18Ni12Mo3Ti			≤0.08	≤1.00	≤2.00	≤0.035	≤0.030	11.00-14.00	16.00-19.00	2.50-3.50	-	-	Ti5*C%-0.70
	28	0Cr18Ni16Mo5	SUS317J1	-	≤0.040	≤1.00	≤2.00	≤0.035	≤0.030	15.00-17.00	16.00-19.00	4.00-6.00	-	-	-
	29	1Cr18Ni9Ti <sup>6)</sup>	-	321	≤0.12	≤1.00	≤2.00	≤0.035	≤0.030	8.00-11.00	17.00-19.00	-	-	-	Ti5(C%-0.02)~0.08
	30	0Cr18Ni10Ti	SUS321	321	≤0.08	≤1.00	≤2.00	≤0.035	≤0.030	9.00-12.00	17.00-19.00	-	-	-	Ti≥5*C%
	31	0Cr18Ni11Nb	SUS347	347	≤0.08	≤1.00	≤2.00	≤0.035	≤0.030	9.00-13.00	17.00-19.00	-	-	-	Nb≥10*C%
	32	0Cr18Ni9Cu3	SUSXM7	XM7	≤0.08	≤1.00	≤2.00	≤0.035	≤0.030	8.50-10.50	17.00-19.00	-	3.00-4.00	-	-
	33	0Cr18Ni13Si4	SUSXM15J1	XM15	≤0.08	3.00-5.00	≤2.00	≤0.035	≤0.030	11.50-15.00	15.00-20.00	-	-	-	2)
	Austenitic ferritic stainless steel	34	0Cr26Ni5Mo2	SUS329J1	-	≤0.08	≤1.00	≤1.50	≤0.035	≤0.030	3.00-6.00	23.00-28.00	1.00-3.00	-	-
35		1Cr18Ni11Si4AlTi	-	-	3.40-4.00	≤0.80	≤0.035	≤0.030	10.--120..	17.50-19.50	-	-	-	Al 0.10-0.30; Ti 0.40-0.70	
36		00Cr18Ni5MoSi2			1.30-2.00	1.00-2.00	≤0.035	≤0.030	4.50-5.50	18.00-19.50	2.50-3.00	-	-	-	
Ferritic stainless steel	37	0Cr13Al	SUS405	405	≤0.08	≤1.00	≤1.00	≤0.035	≤0.030	3)	11.50-14.50	-	-	-	Al 0.10-0.30
	38	00Cr12	SUS410L	-	≤0.030	≤1.00	≤1.00	≤0.035	≤0.030	3)	11.00-13.00	-	-	-	-
	39	1Cr17	SUS430	430	≤0.12	≤0.75	≤1.25	≤0.035	≤0.030	3)	16.00-18.00	-	-	-	-
	40	Y1Cr17	SUS430F	-	≤0.12	≤1.00	≤1.00	≤0.035	≥0.15	3)	16.00-18.00	1)	-	-	-
	41	1Cr17Mo	SUS434	-	≤0.12	≤1.00	≤1.00	≤0.035	≤0.030	3)	16.00-18.00	0.75-1.25	-	-	-
	42	00Cr30Mo2 <sup>5)</sup>	SUS447J1	-	≤0.010	≤0.40	≤0.40	≤0.035	≤0.030	-	28.50-32.00	1.50-2.50	-	≤0.015	-
	43	00Cr27Mo2 <sup>5)</sup>	SUSXM27	XM27	≤0.010	≤0.40	≤0.40	≤0.035	≤0.030	-	25.00-27.50	0.75-1.50	-	≤0.015	-

Type	No.	China GB	JIS	AST M	Chemical composition %										
					C	Si	Mn	P	S	Ni	Cr	Mo	Cu	N	other
Martensitic ferritic stainless steel	44	1Cr12	SUS403	403	≤0.15	≤0.50	≤1.00	≤0.035	≤0.030	3)	11.50-13.00	-	-	-	-
	45	1Cr13	SUS410	410	≤0.15	≤1.00	≤1.00	≤0.035	≤0.030	3)	11.50-13.50	-	-	-	-
	46	0Cr13	SUS405	405	≤0.08	≤1.00	≤1.00	≤0.035	≤0.030	3)	11.50-13.50	-	-	-	-
	47	Y1Cr13	SUS416	-	≤0.15	≤1.00	≤1.25	≤0.035	≥0.15	3)	12.00-14.00	1)	-	-	-
	48	1Cr13Mo	SUS410J	-	≤0.08-0.18	≤0.60	≤1.00	≤0.035	≤0.030	3)	11.50-14.00	0.30-0.60	-	-	-
	49	2Cr13	SUS420J	420	0.16-0.25	≤1.00	≤1.00	≤0.035	≤0.030	3)	12.00-14.00	-	-	-	-
	50	3Cr13	SUS420J2	420	0.26-0.35	≤1.00	≤1.00	≤0.035	≤0.030	3)	12.00-14.00	-	-	-	-
	51	Y3Cr13	SUS420F	-	0.26-0.40	≤1.00	≤1.25	≤0.035	≥0.15	3)	12.00-14.00	1)	-	-	-
	52	3Cr13Mo			0.28-0.35	≤0.80	≤1.00	≤0.035	≤0.030	3)	12.00-14.00	0.50-1.00	-	-	-
	53	4Cr13	-	-	0.36-0.45	≤0.60	≤0.80	≤0.035	≤0.030	3)	12.00-14.00	-	-	-	-
	54	1Cr17Ni2	SUS431	431	0.11-0.17	≤0.80	≤0.80	≤0.035	≤0.030	1.50-2.50	16.00-18.00	-	-	-	-
	55	7Cr17	SUS440A	-	0.60-0.75	≤1.00	≤1.00	≤0.035	≤0.030	3)	16.00-18.00	4)	-	-	-
	56	8Cr17	SUS440B	-	0.75-0.95	≤1.00	≤1.00	≤0.035	≤0.030	3)	16.00-18.00	4)	-	-	-
	57	9Cr18	SUS440C	-	0.90-1.00	≤0.80	≤0.80	≤0.035	≤0.030	3)	17.00-19.00	4)	-	-	-
	58	11Cr17	SUS440C	-	0.95-1.20	≤1.00	≤1.00	≤0.035	≤0.030	3)	16.00-18.00	4)	-	-	-
	59	Y11Cr17	SUS440F	-	0.95-1.20	≤1.00	≤1.25	≤0.035	≥0.15	3)	16.00-18.00	4)	-	-	-
	60	9Cr18Mo	SUS440C	440C	0.95-1.10	≤0.80	≤0.80	≤0.035	≤0.030	3)	16.00-18.00	0.40-0.70	-	-	-
61	9Cr18MoV	-	-	0.85-0.95	≤0.80	≤0.80	≤0.035	≤0.030	3)	17.00-19.00	1.00-1.30	-	-	VO.07-0.12	
PH stainless steel	62	0Cr17Ni4Cu4Nb	SUS630	ASTM A564 M	≤0.07	≤1.00	≤1.00	≤0.035	≤0.030	6.50-7.50	15.50-17.50	-	3.00-5.00	-	Nb 0.15-0.45
	63	0Cr17Ni7Al	SUS631	17700	≤0.09	≤1.00	≤1.00	≤0.035	≤0.030	6.50-7.50	16.00-18.00	-	≤0.50	-	Al 0.75-1.50
	64	0Cr15Ni7Mo2Al			≤0.09	≤1.00	≤1.00	≤0.035	≤0.030	6.50-7.50	14.00-16.00	2.00-3.00	-	-	Al 0.75-1.50



#### Common Questions on Austenitic Stainless Steel Grades:

**Q: What are the equivalent grades for 304 and 316 stainless steel under different standards? A:** According to our component list, 304 is equivalent to 0Cr18Ni9 (GB) and SUS304 (JIS), while 316 corresponds to 0Cr17Ni12Mo2 (GB) and SUS316 (JIS).

**Q: Does Channov Precision provide customized machining for high-temperature alloys like 310S? A:** Yes, we specialize in CNC machining for heat-resistant grades like 310S (0Cr25Ni20) and corrosion-resistant grades like 316L. All components are manufactured according to the precise chemical compositions listed above.

**CHANNOV AUTO PARTS** is a leading manufacturer in the production Oilless Bush, Marginal Lubricating Bush, Bimetal bushing, Bronze Bush, Solid Lubricant Embedded Bush, Cast bronze bearing, Teflon bushing, FR bearing, Door hinge bushing. If you want to know more about material or get a free inquiry, please contact us: [info@channovprecision.com](mailto:info@channovprecision.com), we will reply to you within 2 hours.